GENERAL TECHNOLOGIES, SPC - High-Quality Services & Products

Tel: 816-590-9641, Fax: 253-663-9333 Web: http://gtspc.comEmail: info@gtspc.com

A307 (Formerly 201x7) - OH TYPE I STRONG BASE ANION EXCHANGE RESIN (Designed for use in high purity water applications)

Polymer Structure

Product Description

A307 (OH) resin is a highcapacity Type I strong base anion exchange resin specially designed for use in commercial or industrial demineralized water equipment. The resin removes all anion ions such as sulfate, chloride, bicarbonate, and silica, by replacing them with hydroxide ions. When the resin bed is exhausted the weakest anions (such as silica) begin to pass through the bed. Functionality is returned by regeneration with diluted sodium hydroxide solution.

Typical Physical, Chemical & Operating Characteristics

Polystyrene cross-linked with

Physical Form and Appearance	Divinylbenzene Tough spherical beads
Physical Form and Appearance	rough spherical beaus
Whole Bead Count	90% Min.
Functional Groups	R-N ⁺ (CH ₃) ₃
Ionic Form (as shipped)	OH
Shipping Weight, approx.	660 g/l (41 lb./ft. ³)
Mesh Size (U.S. Std)	16-50
Moisture retention,	< 60%
Swelling, Cl ⁻ to OH ⁻ , %	<20%
Total Capacity in OH ⁻ form	>1.2 meq/ml
pH Range, Stability	0–14

CHEMICAL AND THERMAL STABILITY

A307 (OH) resin is insoluble in dilute or moderately concentrated acids, alkalies, and in all common solvents. However, exposure to significant amounts of free chlorine, "hypochlorite" ions, or other strong oxidizing agents over long periods of time will eventually break down the crosslinking. This will tend to increase the moisture retention of the resin, decreasing it s mechanical strength, as well as generating small amounts of extractable breakdown products. Like all conventional gel type polystyrene Type I strong base anion resins, it is thermally stable to 90°C (195 °F). The hydroxide form tends to degrade in water temperatures appreciably higher than 70°C (160°F), thereby losing capacity, as the functional groups are gradually replaced by hydroxyl groups.