GENERAL TECHNOLOGIES, SPC - High-Quality Services & Products

Tel: 816-590-9641, Fax: 253-663-9333 Web: <u>http://gtspc.com</u>, Email: <u>info@gtspc.com</u>

D890 — CI, WQA/NSF-61 Certified STRONG BASE ANION NITRATE SELECTIVE ION EXCHANGE RESIN (Designed for use in highly selective nitrate removal applications)

Polymer Structure

Product Description

D890 (Cl form) resin is highly nitrateselective due to its unique functional group. In fact, it has higher affinity for monovalent anions (e.g., nitrate) than for di– or tri-valent anions. This is the opposite of the standard Type I and Type II anion resins such as A307 and A302.

In many water treatment applications, D890 is less selective for sulfate than nitrate and nitrate dumping is eliminated. Certain chemical and wastewater treatment processes require a high capacity for monovalent anions than for divalent or trivalent anions.

Because of its unique nature, D890 reverses the electro-selectivity of standard anion resins, and offers preferential removal of anions of lower valence. Particularly, the product can be highly effective in the removal of nitrate in water and wastewater treatment applications even with the presence of high sulfates.

Typical Physical, Chemical & Operating Characteristics

Polystyrene cross-linked with

Polymer Structure	Divinylbenzene
Physical Form and Appearance	Tough spherical beads
Whole Bead Count	90% Min.
Functional Groups	R-N-R₃ ⁺ X⁻
Ionic Form (as shipped)	Cl
Shipping Weight, approx.	700 g/l (44 lb./ft. ³)
Mesh Size (U.S. Std)	16-50
Moisture retention, Na+ form	50-65%
Total Capacity	>1.0 meq/ml
pH Range, Stability	0–14

CHEMICAL AND THERMAL STABILITY

D890 resin is insoluble in dilute or moderately concentrated acids, alkalies, and in all common solvents. However, exposure to significant amounts of free chlorine, "hypochlorite" ions, or other strong oxidizing agents over long periods of time will eventually break down the crosslinking. This will tend to increase the moisture retention of the resin, decreasing it s mechanical strength, as well as generating small amounts of extractable breakdown products. It is thermally stable to higher than 75 °C (170 °F) in the chloride form.



This resin has been tested and certified by WQA according to NSF/ANSI 61 for material requirements only